



COMMERCIAL TESTING COMPANY

1215 South Hamilton Street • Post Office Box 985 • Dalton, GA 30722
Telephone (706) 278-3935 • Facsimile (706) 278-3936

Report Number 09-04429

Turning Star, Inc.
Brooklyn, New York

Test Number 4071-6449-0409R
April 7, 2009

NFPA 701, Test 1

Test Method: The material was tested in accordance with the National Fire Protection Association method NFPA 701, *Standard Methods of Fire Tests for Flame Propagation of Textiles and Films*, 2004 Edition, Test Method 1.

Material Tested: The client submitted a sample of 100% polyester fabric identified as **Georgette Treated with FG-220**. The fabric had a total weight of 3.2 ounces per square yard.

Test Data:

Specimen	After Flame (seconds)	Flaming Dripping (seconds)	Percent Weight Loss
1	0	0	29.1
2	0	0	28.2
3	0	0	7.3
4	0	0	11.2
5	0	0	8.1
6	0	0	25.5
7	0	0	27.4
8	0	0	27.3
9	0	0	29.1
10	0	0	21.0
Mean	N/A	0.0	21.4

Statistical Values:

Standard Deviation = 9.04

Mean + 3 Standard Deviations = 48.5

Performance Criteria: A material passes the test if:

- the average Flaming Dripping time does not exceed 2.0 seconds;
- the average weight loss of the 10 specimens shall be 40 percent or less; and
- no individual specimen's mass loss shall deviate more than 3 standard deviations from the mean.
- Afterflame time is not specified; it is shown for information purposes only.

Test Result: The material tested **MEETS** the requirements of NFPA 701-04, Test 1.

Commercial Testing Company

(Authorized Signature)

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. The test results presented in this report apply only to the samples tested and are not necessarily indicative of apparent identical or similar materials. Sample selection and identification were provided by the client. A sampling plan, if described in the referenced standard, was not necessarily followed. This report, or the name of Commercial Testing Company, shall not be used under any circumstance in advertising to the general public.